



PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>7</sup> :</b> <b>C07D 251/60</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 00/53587</b> <b>(43) International Publication Date:</b> 14 September 2000 (14.09.00)
<b>(21) International Application Number:</b> PCT/NL00/00129 <b>(22) International Filing Date:</b> 2 March 2000 (02.03.00) <b>(30) Priority Data:</b> 99200675.9 8 March 1999 (08.03.99) EP <b>(71) Applicant (for all designated States except US):</b> DSM N.V. [NL/NL]; Het Overloon 1, NL-6411 TE Heerlen (NL). <b>(72) Inventor; and</b> <b>(75) Inventor/Applicant (for US only):</b> TJJOE, Tjay, Tjien [NL/NL]; Hillenraedtstraat 7, NL-6136 BR Sittard (NL). <b>(74) Agent:</b> VAN BOKHOVEN, Petrus, Hubertus, Maria; DSM Patents & Trademarks, P.O. Box 9, NL-6160 MA Geleen (NL).		<b>(81) Designated States:</b> AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
<b>(54) Title:</b> METHOD FOR PREPARING MELAMINE  <b>(57) Abstract</b>  Method for preparing melamine from urea via a high-pressure process in which solid melamine is obtained by transferring the melamine melt to an expansion vessel where the melamine melt is cooled by incorporated ammonia. Excess ammonia gas is added to the melamine melt to produce a gas/liquid mixture having a mass ratio of at least 0.01. This two-phase mixture is then sprayed via a spraying means into an expansion vessel, the expansion vessel having an ammonia environment with a reduced ammonia pressure. The melamine melt is cooled and solidified by the expansion and evaporation of the incorporated ammonia to form melamine powder. The melamine melt is thereby directly converted into a melamine powder after which the melamine powder is cooled further and the ammonia pressure is released.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
C*	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

METHOD FOR PREPARING MELAMINE

5

The invention relates to a method for preparing melamine from urea via a high-pressure process in which solid melamine is obtained by transferring a melamine melt to a vessel where it is cooled with a cooling medium such as ammonia to produce solid high  
10 purity melamine.

Various methods for the production of melamine have been described in previous publications including, inter alia, EP-A-747366 which describes a  
15 high-pressure process for preparing melamine from urea. In particular, EP-A-747366 describes how urea is pyrolyzed in a reactor, operating at a pressure of from 10.34 to 24.13 MPa and a temperature of from 354 to 454°C, to produce a reactor product. This reactor  
20 product, containing liquid melamine, CO<sub>2</sub> and NH<sub>3</sub>, is transferred under pressure as a mixed stream to a separator.

In this separator, the reactor product is separated into a gaseous stream and a liquid stream. The  
25 gaseous stream contains primarily CO<sub>2</sub> and NH<sub>3</sub> waste gases and melamine vapor. The liquid stream mainly comprises a melamine melt. The gaseous stream is transferred to a scrubber unit, while the liquid stream is transferred to a product-cooling unit.

30 In the scrubber unit, the gaseous stream is scrubbed with molten urea. The heat transfer achieved in the scrubber unit both preheats the molten urea and cools the gaseous stream to a temperature from 177 to 232°C. The molten urea also scrubs the gaseous stream to remove  
35 the melamine vapor from the waste gases. The preheated

molten urea, along with the melamine that was scrubbed from the CO<sub>2</sub> and NH<sub>3</sub> waste gases, is then fed into the reactor.

In the product-cooling unit, the melamine melt is cooled and solidified with a liquid cooling medium to produce a solid high purity melamine product without the need for additional purification. The preferred liquid cooling medium is one that forms a gas at the temperature of the melamine melt and at the pressure in the product-cooling unit. EP-A-747366 identifies liquid ammonia as the preferred liquid cooling medium with the pressure in the product-cooling unit being above 4.14 MPa.

Although according to EP-A-747366 the purity of the solid melamine product obtained using the disclosed process was greater than 99 wt%, this degree of purity has proven difficult to maintain continuously on a commercial scale. The inability to maintain a purity greater than 99 wt% is a drawback that renders the melamine produced less suitable for more demanding applications, particularly melamine-formaldehyde resins used in laminates and/or coatings.

Other methods have been suggested to overcome these drawbacks, including among them the applicant's earlier application, WO 98/55466, which used an external spray of liquid ammonia or cool ammonia gas spray to cool the melamine melt, which may be mixed with a minor amount of ammonia gas, as it was sprayed into the cooling vessel. Although this method represented a significant improvement over the prior art methods, the method described in WO 98/55466 still required an external spray of a cooling medium to solidify the melamine. The most efficient cooling of the melamine melt with an external spray, however, depends upon thorough atomization of the

melamine melt (to maximize surface area) and thorough mixing of the atomized melamine melt and the cooling medium spray. A lack of uniformity in the melamine droplet size or spray pattern, and/or non-homogeneous mixing of the droplets and the cooling medium will produce less than optimum results.

Yet another method is taught in WO 97/20826 which provides for the solidification of the melamine through expansion and evaporation of dissolved ammonia. WO 97/20826 teaches the use of relatively high pressures, up to 40 MPa, at temperatures up to 60°C above the melting point of melamine, followed by expansion of the melamine melt at a pressure between 20 MPa and atmospheric pressure. In order to get a quantity of ammonia into solution sufficient to provide the desired cooling, the initial pressures are preferably high and the pressure drop during the relaxation step is large. In general, however, using higher pressures in a commercial plant necessitates increased capital investment in process vessels, piping, and pumps, and results in higher operating costs. It is preferable, therefore, to operate at the lowest possible pressure at which satisfactory results may be obtained.

The object of the present invention is to provide an improved method for preparing melamine from urea, in which melamine is obtained directly from liquid melamine melt as a dry powder having a high degree of purity. More particularly, the object of the present invention is to obtain an improved high-pressure process for preparing melamine from urea, in which melamine is obtained directly from the liquid melamine melt as a dry powder having a high degree of purity by cooling and solidifying via an incorporated cooling medium.

The applicant has found that high purity

melamine can be produced from the melamine melt, which has a temperature between the melting point of melamine and 450°C, preferably less than 45°C, and more preferably less than 30°C above the melting point, by incorporating  
5 sufficient excess ammonia into the melamine melt in an ammonia injection vessel to form a gas/liquid mixture having a gas/liquid mass ratio between 0.01 and 1.0, and preferably between 0.03 and 0.9. This gas/liquid mixture is then sprayed via a spraying means into an expansion  
10 vessel to cool and solidify the melamine by expanding and evaporating the incorporated ammonia in the reduced pressure expansion vessel. The expansion vessel includes an ammonia atmosphere that, although preferably held at a pressure between 0.5% and 60% of the pressure of the  
15 ammonia injection vessel, more preferably between 0.5% and 30% of the pressure of the ammonia injection vessel, is still above atmospheric pressure. The melamine powder thereby obtained may then be cooled further in the expansion vessel, or in a separate cooling vessel, and  
20 the pressure reduced to atmospheric pressure to obtain the final melamine powder product.


In the ammonia injection vessel, ammonia is injected into the melamine melt, the quantity of ammonia injected being more than necessary to saturate the  
25 melamine melt at equilibrium. The excess ammonia is maintained in the melamine melt as ammonia bubbles, the melamine melt and ammonia bubbles forming a two-phase gas/liquid mixture.

In the expansion vessel, the gas/liquid  
30 mixture is rapidly decompressed to cool and solidify the molten melamine. The expansion and vaporization of the excess ammonia in the gas/liquid mixture is sufficient to solidify the melamine without the need for any external cooling medium such as gas or liquid ammonia sprays,

aqueous ammonia solutions, or other cooling means. Further cooling of the solid melamine may, however, be desirable and may be achieved by applying various techniques as disclosed in the prior art, particularly through the introduction of liquid ammonia or cool ammonia gas into the solid melamine.

The advantage of the method according to the present invention is the continuous production, on a commercial scale, of dry melamine powder with a purity above 98.5 wt%, and generally above 99 wt%, that has very good color characteristics. The high purity melamine produced according to the present invention is suitable for virtually any melamine application, including melamine-formaldehyde resins used in laminates and/or coatings. At similar operating conditions, the melamine powder produced according to the present invention provides other advantages over the melamine produced by the prior art processes including reduced particle size, increased surface area, and increased porosity.

The preparation of melamine preferably uses urea as the raw material, the urea being fed into the reactor as a melt and reacted at elevated temperature and pressure. Urea reacts to form melamine, and the by-products  $\text{NH}_3$  and  $\text{CO}_2$ , according to the following reaction equation:



The production of melamine from urea can be carried out at high pressure, preferably between 5 and 25 MPa, without the presence of a catalyst, at reaction temperatures between 325 and 450°C, and preferably between 350 and 425°C. The by-products  $\text{NH}_3$  and  $\text{CO}_2$  are usually recycled to an adjoining urea factory.

The above-mentioned objective of the invention is achieved by employing an apparatus suitable for the preparation of melamine from urea. An apparatus suitable for the present invention may comprise a scrubber unit, a reactor having either an integrated gas/liquid separator or a separate gas/liquid separator, an ammonia injection vessel, an expansion vessel, and possibly additional cooling vessels. It will be appreciated that the configuration of the ammonia injection vessel is not restricted and may, depending on the plant configuration, comprise a portion of the piping between the reactor, or the gas/liquid separator, and the expansion vessel.

In one embodiment of the invention, melamine is prepared from urea in an apparatus comprising a scrubber unit, a melamine reactor having either an integrated gas/liquid separator or a separate gas/liquid separator, an ammonia injection vessel, an expansion vessel, and an optional cooling vessel. In this embodiment, the urea melt is fed into a scrubber unit operating at a pressure of from 5 to 25 MPa, preferably from 8 to 20 MPa, and at a temperature above the melting point of urea. This scrubber unit may be provided with a cooling jacket or internal cooling bodies to provide additional temperature control.

As it passes through the scrubber unit, the urea melt contacts the reaction waste gases coming from the melamine reactor or the separate gas/liquid separator. The reaction gases mainly consist of  $\text{CO}_2$  and  $\text{NH}_3$ , and may include melamine vapor. The urea melt scrubs the melamine vapor from the  $\text{CO}_2$  and  $\text{NH}_3$  waste gases and carries this melamine along back to the reactor. In the scrubbing process, the waste gases are cooled from the temperature of the reactor, i.e., from 350 to 425°C, to



from 170 to 240°C, the urea being heated to from 170 to 240°C. The CO<sub>2</sub> and NH<sub>3</sub> waste gases are removed from the top of the scrubber unit and may, for example, be recycled to an adjoining urea factory, where they can be used as raw materials for the urea production.

The preheated urea melt is drawn off from the scrubber unit, together with the melamine scrubbed from the waste gases, and transferred to the high pressure reactor operating at pressures between 5 and 25 MPa, and preferably between 8 and 20 MPa. This transfer may be achieved using a high-pressure pump or, where the scrubber is positioned above the reactor, by gravity, or a combination of gravity and pumps.

In the reactor, the urea melt is heated to a temperature between 325 and 450°C, preferably between about 350 and 425°C, under a pressure between 5 and 25 MPa, preferably between 8 and 20 MPa, to convert the urea into melamine, CO<sub>2</sub> and NH<sub>3</sub>. In addition to the urea melt, a certain amount of ammonia can be metered into the reactor as, for example, a liquid or hot vapor. The additional ammonia, although optional, may serve, for example, to prevent the formation of condensation products of melamine such as melam, melem and melon, or to promote mixing in the reactor. The amount of additional ammonia supplied to the reactor may be up to 10 moles ammonia per mole of urea, preferably up to 5 moles ammonia per mole of urea, and, most preferably, up to 2 moles of ammonia per mole of urea.

The CO<sub>2</sub> and NH<sub>3</sub> produced in the reaction, as well as any additional ammonia supplied, collect in the separation section, for example in the top of the reactor or in a separate gas/liquid separator positioned downstream of the reactor, and are separated from the liquid melamine. If a separate, downstream gas/liquid

separator is used, it may be advantageous for additional ammonia to be metered into this separator. The amount of ammonia in this case is 0.01-10 moles of ammonia per mole of melamine, and preferably 0.1-5 moles of ammonia per mole of melamine. Adding additional ammonia to the separator promotes the rapid separation of carbon dioxide from the reactor product, thus preventing the formation of oxygen-containing by-products. As described above, the gas mixture removed from the gas/liquid separator may be passed to the scrubber unit in order to remove melamine vapor and preheat the urea melt.

The melamine melt, having a temperature between the melting point of melamine and 450°C, is drawn off from the reactor, or from the downstream gas/liquid separator, and optionally cooled, is then fed into an ammonia injection vessel. In the ammonia injection vessel, excess ammonia is added to the melamine melt to produce a gas/liquid mixture in which ammonia is present both in solution and as a separate gas phase. Sufficient ammonia is added to produce a two-phase stream in which the gas/liquid mass ratio is between 0.01 and 1.0, and preferably between 0.03 and 0.9. This gas/liquid mixture is then sprayed into an expansion vessel to obtain the solid melamine product.

Prior to spraying in the expansion vessel, however, the melamine melt may be cooled from the reactor temperature or gas/liquid separator temperature to a temperature closer to, but still above, the melting point of melamine. The melamine melt, which is drawn off from the reactor at a temperature typically above 380°C, may be cooled to a temperature preferably not more than 45°C, and more preferably not more than 30°C, above the melamine melting point before being sprayed into the expansion vessel. The lower the temperature of the melt

before expansion, the lesser ammonia is needed for cooling and solidifying the melamine melt in the expansion vessel. The melamine melt may be cooled in the gas/liquid separator, the ammonia injection vessel, or in  
5 an additional apparatus positioned downstream from the reactor and before the expansion vessel. It is contemplated that cooling can take place by injection of a cooling medium, for example ammonia gas having a temperature below the temperature of the melamine melt,  
10 or by passing the melamine melt through a heat exchanger.

The melamine and ammonia mixture, is transferred to a spraying means as a two-phase mixture and there it is sprayed through a spraying means into an expansion vessel to solidify the melamine and form a dry  
15 melamine powder. The spraying means is an apparatus by which the gas/liquid mixture is converted into droplets, by causing the melt to flow at high speed into the expansion vessel. The spraying means may be a nozzle or valve. The outflow velocity of the gas/liquid mixture  
20 from the spraying means is, as a rule, greater than 20 m/s, and is preferably greater than 50 m/s. The outflow velocity is defined as the nominal volumetric flow of the mixture (in  $\text{m}^3/\text{s}$ ) divided by the smallest cross sectional flow area in the nozzle or valve (in  $\text{m}^2$ ).

25 The expansion vessel contains an ammonia environment and operates at an increased ammonia pressure. The melamine droplets from the spraying means are cooled by energy transfer from the molten melamine to the expanding and evaporating ammonia to produce melamine  
30 powder. The melamine powder thus formed can have a temperature between  $100^\circ\text{C}$  and the solidification point of melamine, and preferably below  $300^\circ\text{C}$ .

In another embodiment of the present invention the melamine powder formed by spraying the

gas/liquid mixture into the expansion vessel is held in the expansion vessel for a predetermined contact time under an increased ammonia pressure and at a temperature above 200°C. The duration of this contact time is preferably between 5 minutes and 2 hours. During this contact time, the temperature of the melamine product can remain virtually constant or it may be cooled to a temperature above 200°C. Additional cooling of the solidified melamine may be effected through the addition of cool ammonia gas or liquid ammonia, separately or in combination with mechanical agitation and indirect cooling through contact with cooled surfaces. Examples of means for mechanically agitating the melamine powder include a screw and rotating drum, a rotating bowl, rotating discs, rotating segmented discs, rotating pipes and the like.

Once the melamine powder has been cooled to a temperature below 200°C, the ammonia pressure may be released. Preferably, the ammonia gas is completely removed (to an amount below 1000 ppm, preferably below 300 ppm, and, most preferably, below 100 ppm) by blowing air through the melamine powder. The ammonia pressure may be released before, or in conjunction with, cooling the melamine powder from a temperature below 200°C to ambient temperature.

The invention will be explained in more detail with reference to the following examples and comparative examples.

#### 30 Example I

To a melamine melt, which is saturated with ammonia at a temperature of 359 °C and a pressure of 20.4 MPa, additional ammonia gas with the same temperature is added. The liquid flow is 4.8 kg/hour and the additional

ammonia gas flow is 1.4 kg/hour. This two-phase flow is depressurized in a vessel wherein an ammonia pressure of 2.5 MPa is maintained, resulting in solidification of the melamine melt. The melamine melt is further cooled with liquid ammonia and the vessel is depressurized. The product has a melamine purity of 99.6%.

#### Example II

To a melamine melt, which is saturated with ammonia at a temperature of 353 °C and a pressure of 17.9 MPa, additional ammonia gas with the same temperature is added. The liquid flow is 4.8 kg/hour and the additional ammonia gas flow is 0.9 kg/hour. This two-phase flow is depressurized in a vessel with an ammonia pressure of 1.8 MPa, resulting in solidification of the melamine melt. The melamine melt is further cooled with liquid ammonia and the vessel is depressurized. The product has a melamine purity of 99.2%.

#### Comparative example A

The same experiment as mentioned in example I is performed without the additional ammonia gas flow. So only a single phase melamine melt is depressurized in the quench vessel. The product has a melamine purity of 98.7%.

#### Comparative example B

The same experiment as mentioned in example II is performed without the additional ammonia gas flow. So only a single phase melamine melt is depressurized in the quench vessel. The product has a melamine purity of 98.5%.

C L A I M S

1. Method for preparing melamine from urea via a high-pressure process characterized in that, high purity  
5 melamine can be produced from the melamine melt, which has a temperature between the melting point of melamine and 450°C, by incorporating sufficient excess ammonia into the melamine melt in an ammonia injection vessel to form a two-phase gas/liquid  
10 mixture, the gas/liquid mixture having a gas/liquid mass ratio of between 0.01 and 1.0, thereafter spraying the gas/liquid mixture via spraying means into an expansion vessel to cool and solidify the melamine by expanding and evaporating of the  
15 incorporated ammonia in the reduced pressure expansion vessel.
2. Method according to Claim 1, characterized in that the gas/liquid mass ratio is between 0.03 and 0.9.
3. Method according to either one of Claims 1-2,  
20 characterized in that the temperature of the melamine melt being sprayed into the expansion vessel is between the melting point of melamine and a temperature 45°C above the melting point of melamine.
- 25 4. Method according to either one of Claims 1-3, characterized in that the temperature of the melamine melt being sprayed into the expansion vessel is between the melting point of melamine and a temperature 30°C above the melting point of  
30 melamine.
5. Method according to Claims 1-4, characterized in that the expansion vessel include an ammonia pressure held between 0.5% and 60% of the pressure of the ammonia injection vessel.

6. Method according to Claims 1-4, characterized in that the expansion vessel include an ammonia pressure held between 0.5% and 30% of the pressure of the ammonia injection vessel.
- 5 7. Method according to Claims 1-6, characterized in that the configuration of the ammonia injection vessel comprise a portion of the piping between the reactor or the gas/liquid separator and the expansion vessel.
- 10 8. Method according to Claims 1-7, characterized in that the outflow velocity of the gas/liquid mixture from the spraying means is greater than 50 m/sec.
9. Method according to Claims 1-8, characterized in that the ammonia pressure is released if the  
15 melamine powder has a temperature below 200°C.
10. Method for the preparation of melamine as substantially described in the specification and the examples.

## INTERNATIONAL SEARCH REPORT

International Application No

PCT/NL 00/00129

**A. CLASSIFICATION OF SUBJECT MATTER**  
IPC 7 C07D251/60

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C07D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 98 52928 A (DSM NV ; TJIOE TJAY TJIEN (NL)) 26 November 1998 (1998-11-26) page 6, line 9-15, paragraph 2 page 7, line 18-22,27-29, paragraph 3	1
X	US 5 731 437 A (OINAS PEKKA ET AL) 24 March 1998 (1998-03-24) column 4, line 54,55,63-65, paragraph 4	1
X	claim 10 column 5, line 3-7,54,55	1
X	WO 97 34879 A (DSM NV ; HAAN ANDRE BANIER DE (NL); SAMPERS THEODORUS JOSEPHUS ANN) 25 September 1997 (1997-09-25) page 4, line 1-6, paragraph 1 page 5, line 35,36	1

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

## \* Special categories of cited documents :

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

\*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

\*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

\*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

\*Z\* document member of the same patent family

Date of the actual completion of the international search

30 June 2000

Date of mailing of the international search report

10/07/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 851 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Goss, I



## INTERNATIONAL SEARCH REPORT

International Application No

PCT/NL 00/00129

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	WO 98 54160 A (DSM NV ;SLANGEN HUBERTUS JOZEF MARIA (NL); TJIOE TJAY TJIEN (NL)) 3 December 1998 (1998-12-03) page 6, line 29 -page 7, line 5 page 8, line 14-16, paragraph 2	1
Y	WO 97 47609 A (DSM NV ;WIJCK JULIUS GERARDUS THEODORU (NL)) 18 December 1997 (1997-12-18) page 10, line 30-35	1
Y	EP 0 808 836 A (DSM NV) 26 November 1997 (1997-11-26) column 4, line 38-44, paragraph 5	1
A	EP 0 747 366 A (MELAMINE CHEMICALS INC) 11 December 1996 (1996-12-11) cited in the application the whole document	
A	WO 98 55466 A (DSM NV ;SLANGEN HUBERTUS JOZEF MARIA (NL); TJIOE TJAY TJIEN (NL)) 10 December 1998 (1998-12-10) cited in the application the whole document	1
A	US 5 721 363 A (MUELLNER MARTIN ET AL) 24 February 1998 (1998-02-24) the whole document column 1, line 60-63	1

## INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No.

PCT/NL 00/00129

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 9852928	A	26-11-1998	NL 1006095 C	25-11-1998
			AU 7555398 A	11-12-1998
			EP 0983250 A	08-03-2000
			NO 995694 A	19-11-1999
US 5731437	A	24-03-1998	FI 933033 A	02-01-1995
			AT 187446 T	15-12-1999
			DE 69422039 D	13-01-2000
			DE 69422039 T	25-05-2000
			EP 0706519 A	17-04-1996
			ES 2141238 T	16-03-2000
			WO 9501345 A	12-01-1995
			JP 8512042 T	17-12-1996
WO 9734879	A	25-09-1997	NL 1002669 C	23-09-1997
			AU 715825 B	10-02-2000
			AU 1947597 A	10-10-1997
			CN 1218458 A	02-06-1999
			EP 0888315 A	07-01-1999
			NO 984324 A	17-11-1998
			PL 328914 A	01-03-1999
WO 9854160	A	03-12-1998	NL 1006147 C	01-12-1998
			AU 7555498 A	30-12-1998
			EP 0984946 A	15-03-2000
			NO 995816 A	26-01-2000
WO 9747609	A	18-12-1997	NL 1003328 C	17-12-1997
			AU 720041 B	25-05-2000
			AU 3108597 A	07-01-1998
			CA 2258162 A	18-12-1997
			CN 1227549 A	01-09-1999
			EP 0920420 A	09-06-1999
			NO 985744 A	29-01-1999
			PL 330866 A	07-06-1999
EP 0808836	A	26-11-1997	NL 1003105 C	18-11-1997
			CN 1170720 A	21-01-1998
			JP 10045730 A	17-02-1998
EP 0747366	A	11-12-1996	US 5514796 A	07-05-1996
			AU 706404 B	17-06-1999
			AU 5473296 A	19-12-1996
			BR 9602673 A	10-11-1998
			CA 2177521 A	08-12-1996
			JP 9012559 A	14-01-1997
			NO 962339 A	09-12-1996
			NZ 286589 A	27-04-1998
			PL 314673 A	09-12-1996
			ZA 9603945 A	10-12-1996
WO 9855466	A	10-12-1998	NL 1006192 C	03-12-1998
			AU 7555698 A	21-12-1998
			EP 0986547 A	22-03-2000
			NO 995886 A	26-01-2000
US 5721363	A	24-02-1998	AT 402294 B	25-03-1997
			AT 239294 A	15-08-1996

## INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/NL 00/00129

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5721363 A		AT 176228 T	15-02-1999
		AU 692034 B	28-05-1998
		AU 4386196 A	19-07-1996
		BG 101594 A	27-02-1998
		BR 9510363 A	23-12-1997
		CA 2207059 A	04-07-1996
		CN 1171102 A	21-01-1998
		DE 59505010 D	11-03-1999
		WO 9620182 A	04-07-1996
		EP 0799212 A	08-10-1997
		ES 2128798 T	16-05-1999
		HR 950607 A	31-10-1997
		HU 77060 A, B	02-03-1998
		JP 10511368 T	04-11-1998
		NO 972869 A	14-08-1997
		NZ 298387 A	29-04-1999
		PL 320789 A	27-10-1997
		SK 79297 A	08-10-1997
		TR 960596 A	21-07-1996
		ZA 9510900 A	24-06-1996